

Product Description:

ELASTI-THANE BASECOAT is a high solids, 2-component, aliphatic polyurethane designed to perform multiple functions. It provides the benefits of UV stability with the ability to be extended to almost any thickness when incorporating Rock-Tred aggregates and fillers.

ELASTI-THANE BASECOAT can be used as a stand-alone flexible grout or as the base coat for Rock-Tred foot traffic membrane systems for use in mechanical equipment rooms, mezzanines, porches and walkways, etc. **ELASTI-THANE BASECOAT** can be left as the finish coat or can be top coated with ELASTI-THANE TOPCOATS for added protection and beauty.

Physical Testing Information:

Volume mix ratio:	Mix entire content of kit
Viscosity [mixed]	4000-6000 CPS Typical
Solids Content (%):	96% [ASTM D-2697]
Ultimate Elongation (ASTM D412)	1,000-1,200 %
Abrasion Resistance	Tabor 1000 cycles / CS 17 wheel / 100g 0.02 grams Loss
Tensile Strength (ASTM D412)	700-800 psi
Hardness (ASTM C-661)	60-65 (Shore A)
Application Temps:	33 ^o – 80 ^o F
Pot-life	35-40 minutes @ 75 ^o F (24 ^o C)
Recoat time	6-8 hours @ 75 ^o F (24 ^o C)
'Open' to foot traffic	12-16 hours @ 75 ^o F (24 ^o C)
'Open' to vehicle traffic	36+ hours @ 75 ^o F (24 ^o C)
Shelf Life	6 months in unopened unit

Please review ROCK-TRED's Product Data Sheet and SDS for further information on this product. All physical testing information is from performance testing run on neat coats of the tested product unless otherwise indicated.